

AAG M22 ISOLERENDE MÅTTE

teknisk datablad



PROPERTIES	DESCRIPTION
Material	Microporous closed cell Ethylene Vinyl Acetate
Colour	Standard = Black
Thickness	22 mm
Density	0.2g/cm ³ ± 0.02
Hardness	Shore A 30-37
Stability 1. Thermal 2. Physical 3. Chemical	Elevated temperatures over 40°C will cause shrinkage e.g. in intense sunshine. Slight expansion occurs in the initial period of usage. E.V.A. is more stable than rubber polymers. It offers good/excellent resistance to acids/bases/alcohols.
Flammable	Yes, when exposed to flame. Auto-ignition is in excess of 200°C
Electrical Conductivity	No. It is an insulator
Thermal Insulation	U values not available but it is an excellent heat insulator

OBS!

AAG M22 Isolerende måtte er til brug i smågrisehuler. Ingen garanti mod soens adfærd (bid osv.) og mekanisk slid. Måtten må ikke rengøres med turbojetdyse eller udsættes for direkte sollys eller varme. Folie skal fjernes ved modtagelse.

FORBEHOLD:

AAG er ikke ansvarlig for evt. følgeskader, som er opstået af, at gulvvarme eller anden varmekilde slukkes. Hvorvidt der kan ydes energitilskud er en sag mellem energiselskabet og den enkelte landmand.

