

AAG CHECKER MAT

datasheet 3 mm



NR-SBR, black – commercial
matting with hammerblow surface
(one side hammerblow design, one side fabric
impression)
packaging see General Information

Hardness [Shore A]: 70 ±7
Density [g/cm³]: approx. 1.46
Tensile strength [N/mm²]: 4
Elongation at break [%]: 200
Ozone resistance: non resistant
Weather resistance: non resistant
Oil resistance: non resistant
Benzine resistance: non resistant
Acid resistance: moderately resistant
Strong bases: moderately resistant
Abrasion resistance: non suitable

WORKING TEMPERATURE RANGE


Medium	dyn. (stat.)	max.	short-term
Air	-10 (-30) °C	+70 °C	+90 °C

COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	40 %

ROTA-CURED-SHEETS

Article- number	Thickness mm	Width m	Length m	No. of insert.
4024 99050	3.0	1.4	10	0
4024 99035	3.0	1.25	10	0
4024 99054	5.0	1.4	10	0
4024 99070	5.0	1.25	10	0



Please Note:

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.